


**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

Claim 1. (canceled).

Claim 2. (currently amended): A sol ~~in which~~comprising dispersed said perovskite titanium-containing composite oxide particle ~~as claimed in claim 1~~having a composition represented by general formula (I), wherein the specific surface area is about 10 to about 200 m<sup>2</sup>/g, the specific surface area diameter D<sub>1</sub> of primary particles defined by formula (II) is about 10 to about 100 nm, and a D<sub>2</sub>/D<sub>1</sub> ratio of the average particle size D<sub>2</sub> of secondary particles to D<sub>1</sub> is about 1 to about 10:




wherein M is at least one of Ca, Sr, Ba, Pb, or Mg and

$$D_1 = 6/\rho S \text{ --- (II)}$$


wherein  $\rho$  is the density of the particles, and S is the specific surface area of the  
particles~~is dispersed.~~

Claim 3. (currently amended): A process for producing a sol in which a perovskite titanium-containing composite oxide particle represented by general formula (I) is dispersed, comprising the step of allowing a titanium oxide particle comprising a brookite crystalline form to react with a metal salt comprising at least one of Ca, Sr, Ba, Pb, or Mg in a liquid phase:



{wherein M is at least one of Ca, Sr, Ba, Pb, or Mg}.

Claim 4. (currently amended): A process for producing a sol in which a perovskite titanium-containing composite oxide particle represented by general formula (I) is dispersed, comprising the step of allowing a titanium oxide sol prepared by subjecting a titanate to hydrolysis in an acid solution to react with a metal salt comprising at least one of Ca, Sr, Ba, Pb, or Mg in a liquid phase:



{wherein M is at least one of Ca, Sr, Ba, Pb, or Mg}.

Claim 5. (currently amended): A sol obtained by said production process as claimed in claim 3 **[[4]]**.

Claim 6. (canceled).

Claim 7. (currently amended): The production process of said sol as claimed in claim 3 **[[or 4]]**, wherein said liquid phase is alkaline.

Claims 8-16. (canceled).

Claim 17. (new): A sol obtained by said production process as claimed in claim 4.

Claim 18. (new): The production process of said sol as claimed in claim 4, wherein said liquid phase is alkaline.

Claim 19. (new): The sol as claimed in claim 2, wherein the specific surface area of the perovskite titanium-containing composite oxide particle is 28 to about 200 m<sup>2</sup>/g.

Claim 20. (new): The sol as claimed in claim 2, wherein the diameter  $D_1$  of primary particles defined by formula (II) is about 10 to 50 nm.